



US006344155B1

(12) **United States Patent**
Kitahara et al.

(10) **Patent No.:** **US 6,344,155 B1**
(45) **Date of Patent:** **Feb. 5, 2002**

(54) **ELECTRICALLY CONDUCTIVE ADHESIVE COMPOSITION, ELECTRICALLY CONDUCTIVE ADHESIVE SHEET AND USE THEREOF**

(75) Inventors: **Hiroshi Kitahara; Kensaku Higashi,**
both of Shizuoka (JP)

(73) Assignee: **Tomoe-gawa Paper Co., Ltd.,** Tokyo
(JP)

(*) Notice: Subject to any disclaimer, the term of this
patent is extended or adjusted under 35
U.S.C. 154(b) by 0 days.

(21) Appl. No.: **09/541,716**

(22) Filed: **Apr. 3, 2000**

(30) **Foreign Application Priority Data**

Apr. 6, 1999 (JP) 11-098500
Jan. 28, 2000 (JP) 12-019583

(51) **Int. Cl.⁷** **H01B 1/04**

(52) **U.S. Cl.** **252/502; 252/512; 442/6;**
442/117

(58) **Field of Search** 252/512, 502;
442/117, 6

(56) **References Cited**

U.S. PATENT DOCUMENTS

3,989,531 A * 11/1976 Orlando et al. 524/288
4,742,104 A * 5/1988 Lindner et al. 525/74
5,399,295 A * 3/1995 Gamble et al. 252/511
5,530,044 A * 6/1996 Mack et al. 524/366
5,736,070 A * 4/1998 Murakami et al. 252/512

* cited by examiner

Primary Examiner—Cathy Lam

(74) *Attorney, Agent, or Firm*—Wenderoth, Lind & Ponack,
LLP

(57) **ABSTRACT**

An electrically conductive adhesive composition which has flexibility and folding endurance and is feasible for use as a shield against electromagnetic waves from a flexible printed circuit, comprises 100 parts by weight of (a) an acrylonitrile-butadiene copolymer, 20 to 500 parts by weight of (b) a phenolic resin and/or an epoxy resin, 1 to 100 parts by weight, per 100 parts by weight of the components (a) and (b) in total, of (c) an electrically conductive filler and 1 to 50 parts by weight, per 100 parts by weight of the components (a) and (b) in total, of (d) a bromine-containing flame retardant.

18 Claims, No Drawings